

PRODUCT DATA SHEET

Avery Dennison® Polyester Films

issued: 08/2016

Introduction

Avery Dennison Polyester films is a range of products that are used for a wide variety of graphics.

Description

Facefilms: surface treated polyester.
Avery Dennison 710 – gloss transparent
Avery Dennison 710 – gloss chrome
Avery Dennison 711 – satin chrome

Availability

| | | |
|--|------------|-----------|
| | Adhesive ☞ | Permanent |
| Backing (white two-side polyethylene coated kraft paper) | ☝ | |
| Standard | | x |

Conversion

Avery Dennison Polyester films can be printed in screen printing, offset litho and letterpress. Each process requires special inks and processing conditions. Ask your ink manufacturer for detailed processing procedures.

Features

- High tensile strength films
- Excellent solvent and chemical resistance
- Excellent adhesion to a wide range of substrates
- Bright Silver colour, enhancing luxury appearance
- Attractive 'brushed metal' appearance of Avery Dennison 772
- Durable, permanent adhesive
- High transparency of Avery Dennison 710 Transparent

Recommendations for use

- Double sided window stickers
- Nameplates and decorative trim
- Product labels and serial numbers
- Bicycle decorations
- Printed/unprinted graphics

PRODUCT CHARACTERISTICS

Avery Dennison® Polyester Films

Physical properties

| Features | Test method ¹ | Results |
|---|----------------------------|--------------------|
| Caliper, facefilm – Avery Dennison 710 | ISO 534 | 23 micron |
| Caliper, facefilm – Avery Dennison 711 | ISO 534 | 24 micron |
| Dimensional stability Avery Dennison 710/711 | DIN 30646 | 0.1 mm max. |
| Flammability | | Self extinguishing |
| Shelf life | Stored at 22° C/50-55 % RH | 2 years |
| Durability ² 710 Transparent | Vertical exposure | 2 years |
| 710 Chrome / 711 Satin Chrome | | 2 years |

Adhesives

Permanent A glass clear, acrylic-based adhesive for maximum sunlight and weather resistance.
Good initial tack and ultimate adhesion.

| | <u>Permanent</u> | |
|---------------------------------------|--|-------|
| Minimum application temperature | +10 °C | |
| Service temperature range | -20 °C to +80 °C (24hrs) +110 °C (1hr) | |
| Adhesion on stainless steel, initial | 550 N/m | FTM-1 |
| Adhesion on stainless steel, ultimate | 750 N/m | FTM-1 |

Chemical properties

| Features | Test method ¹ | Results |
|----------------------|----------------------------|---|
| Humidity resistance | 120 hours exposure | No effect |
| Corrosion resistance | 120 hours exposure | No contribution to corrosion |
| Water resistance | 48 hours immersion | No effect |
| Chemical resistance | Mild acids Mild alkalis | No effect No effect |
| Solvent resistance | Applied to aluminium | No effect if exposed to: oils, greases, aliphatic solvents, motor oils, heptane, kerosene and JP-4 fuel. |

Important

Information on physical and chemical characteristics is based upon tests we believe to be reliable. The values listed herein are typical values and are not for use in specifications. They are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine, prior to use, the suitability of this material to their specific use.
All technical data are subject to change without notice.

Warranty

All Avery Dennison statements, technical information and recommendations are based on tests believed to be reliable but do not constitute a guarantee or warranty. All Avery Dennison products are sold with the understanding that purchaser has independently determined the suitability of such products for its purposes. All Avery Dennison's products are sold subject to Avery Dennison's general terms and conditions of sale, see

<http://terms.europe.averydennison.com>

1) Test methods

More information about our test methods can be found on our website.

2) Durability

The durability is based on middle European exposure conditions. Actual performance life will depend on substrate preparation, exposure conditions and maintenance of the marking. For instance, in the case of signs facing south; in areas of long high temperature exposure such as southern European countries; in industrially polluted areas or high altitudes, exterior performance will be decreased.
