

**Ritrama S.p.A.**

Legal Head Office & Administrative Office
Via Senatore Simonetta, 24
20867 Caponago (MB) - Italy
TAX/VAT: IT01676140153
Share Capital: 8.824.950 EUR i.v.
Reg. Imp. MB - Monza e Brianza Comp. Reg.
R.E.A. n. 1871535
info@ritrama.com - www.ritrama.com

ROLL Slitting & Logistic Centre
GRAPHICS Slitting & Logistic Centre
Via Senatore Simonetta, 24
20867 Caponago (MB) - Italy
Ph: +39 02 955 45 91
Fax: +39 02 955 45 901

Production Centre
Polo Industriale Berbentina
60041 Sassoferrato (AN) - Italy
Ph: +39 0732 970 61
Fax: +39 0732 964 36

Production Centre
Viale Industrie, 30
20060 Basiglio (MI) - Italy
Ph: +39 02 923 948 1
Fax: +39 02 923 948 39

Caponago 20/03/2019

RI-121/200 Slip Resistance approval

01346 RI-121/200 FLOOR TALKER CLEAR ASP8A PERMANENT WG90 overlamine film has been tested in accordance with the guidelines recommended by the UK Slip Resistance Group:

<http://www.ukslipresistance.org.uk/index.php?id=guidelines>

“The Assessment of Floor Slip Resistance” - Issue 3 2005.

The UK Slip Resistance Group comprises members from flooring and associated industries and includes flooring manufacturers, representatives of the Health and Safety Executive, test houses, end users, instrument manufacturers, and forensic engineers.

Standard reference: DIN 51130:2010 Testing of Floorcoverings – Determination of Slip resistance work rooms and areas of work with an increased risk of slipping - Walking method - Ramp test.

Test	Inclined Platform Shod
Mean Value	10.1°
Rating	R10

R rating category:

R value	Category Static Friction is:	Angle of Inclination
R9	Low	6° to 10°
R10	Normal	10,1° to 19°
R11	Above Average	19.1° to 27°
R12	High	27.1° to 35°
R13	Very High	> 35°

Note to end use applications:

R9 Floors in work rooms and work areas without a high risk of slipping. General and private areas.

R10 to R13 Floors in workrooms and work areas where there is an increased risk of slipping due to grease, oil, water, foods, left-overs, dust, flour, plant clippings, etc..