

February, 2019

3M™ Scotch-Weld™ Epoxy Adhesive DP190 Gray

Product Description

3M™ Scotch-Weld™ Epoxy Adhesive DP190 Gray is a 1:1 by volume mix ratio of 3M™ Scotch-Weld™ Epoxy Adhesive 2216 B/A Gray and exhibits good peel, shear and environmental aging properties. Available in bulk containers as 3M™ Scotch-Weld™ Epoxy Adhesive 2216 B/A.

Product Features

- 90 minute worklife
- High shear and peel strength
- Flexible
- 1:1 mix ratio
- Gray
- Recognized as meeting UL 94 HB



Technical Information Note

The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Uncured Physical Properties

Property	Values	Notes	Test Condition
Color	Gray	Colors may vary from nearly white to yellow/amber. Adhesive performance is not affected by color variation.	
Base Color	White		
Accelerator Color	Gray		
Base Viscosity	75,000-150,00 cP		Room Temperature
Accelerator Viscosity	40,000-80,000 cP		Room Temperature
Base Resin	Epoxy		
Accelerator Resin	Amine		
Base Net Weight	11.0 to 11.4 lb/gal		
Accelerator Net Weight	10.6 to 11.0 lb/gal		
Mix Ratio by Volume (B:A)	1:1		
Mix Ratio by Weight (B:A)	1.06:1		

Typical Mixed Physical Properties

Property	Values	Method	Test Condition	Notes	Substrate
Worklife	90 min	3M C3180	Room Temperature	Procedure involves periodically measuring a 2 gram mixed mass for self leveling and wetting properties. This time will also approximate the usable worklife in an 3M™ EPX™ Applicator mixing nozzle.	

Table continued on next page

Typical Mixed Physical Properties (continued)

Property	Values	Method	Test Condition	Notes	Substrate
Worklife, 20g mixed	90 min	3M C3180	Room Temperature	Procedure involves periodically measuring a 2 gram mixed mass for self leveling and wetting properties. This time will also approximate the usable worklife in an 3M™ EPX™ Applicator mixing nozzle.	
Tack Free Time	6 h	3M C3173		Involves dispensing 0.5 gram amount of adhesive onto substrate and testing periodically for no adhesive transfer to metal spatula.	
Time to Handling Strength	8 to 12 h	3M C3179		Time to handling strength taken to be that required to achieve a 50 psi overlap shear (OLS) strength using aluminum substrates.	Aluminum
Time to Full Cure	7 day			The cure time is defined as that time required for the adhesive to achieve a minimum of 80% of the ultimate strength as measured by aluminum-aluminum OLS.	

Rate of Strength Buildup	Dwell/Cure Time	Dwell Time Units
10 lb/in ²	1	hr
50 lb/in ²	6	hr
1000 lb/in ²	1	day
2000 lb/in ²	7	day
2200 lb/in ²	1	month
2500 lb/in ²	3	month

Property: Rate of Strength Buildup

Method: ASTM D1002

Attribute Modifier: Overlap Shear Strength

Temp C: 22C

Temp F: 72F

Substrate: Etched Aluminum

Substrate Notes: 0.005-0.008in bondline

notes: Overlap shear (OLS) strengths were measured on 1 in. wide 1/2 in. overlap specimens. These bonds were made individually using 1 in. x 4 in. pieces of substrate. The separation rate of the testing jaws was 0.1 in. per minute for metals, 2 in. per minute for plastics and 20 in. per minute for rubbers. The thickness of the substrates were: steel, 0.060 in.; other metals, 0.05-0.064 in.; rubber, 0.125 in.; plastics, 0.125 in.

Typical Cured Characteristics

Property	Values	Method	Dwell/Cure Time	Notes	Test Condition
Tensile Strength	3500 lb/in ²	ASTM D882	2 hr Room Temperature, plus 2 hr @ 160°F(71°C)	Samples were 2" dumbbells with .0125" neck and .030" sample thickness. Separation rate was 2 inches per minute.	
Shore D Hardness	60	ASTM D2240	60 min @ Room Temperature		
Weight Loss by Thermal Gravimetric Analysis (TGA)	1%	ASTM E1131		Weight loss by Thermal Gravimetric Analysis reported as that temperature at which 5% weight loss occurs by TGA in air at 5°C (9°F) rise per minute.	477°F(247°C)
Weight Loss by Thermal Gravimetric Analysis (TGA)	5%	ASTM E1131		Weight loss by Thermal Gravimetric Analysis reported as that temperature at which 5% weight loss occurs by TGA in air at 5°C (9°F) rise per minute.	639°F(337°C)
Thermal Shock Resistance	Pass 5 cycles without cracking	3M C3174		Involves potting a metal washer into a 2 in. x 0.5 in. thick section and cycling this test specimen to colder and colder temperatures.	Potted Washer Olyphant Test, 100°C [air] to -50°C [liquid]

Typical Physical Properties

Color: Gray

Conditions

Attribute Modifier: Cured

Typical Performance Characteristics

Elongation: 30 %

Conditions

Dwell/Cure Time: 2 hr Room Temperature, plus 2 hr @ 160°F(71°C)

Methods

ASTM D882

Additional Information

Notes: Samples were 2 in. dumbbells with 0.125 in. neck and .030 in. sample thickness. Separation rate was 2 inches per minute.

3M™ Scotch-Weld™ Epoxy Adhesive DP190 Gray

Typical Performance Characteristics (continued)

T-Peel Adhesion	Temp C	Temp F
3 lb/in width	-55C	-67F
20 lb/in width	23C	73F
10 lb/in width	49C	120F
4 lb/in width	66C	150F
2 lb/in width	82C	180F

Property: T-Peel Adhesion

Method: ASTM D1876

Substrate: Etched Aluminum

Substrate Notes: 0.005-0.008in bondline

notes: T-peel strengths were measured on 1 in. wide bonds at 73°F (23°C). The testing jaw separation rate was 20 inches per minute. The substrates were 0.020 in. thick. Samples dwelled for 24 hrs at 23C + 2 hrs at 71C before testing.

Solvent Resistance	Environmental Condition
A	Immersed in Acetone one hour
A	Immersed in Acetone one month
A	Immersed in Isopropyl Alcohol one hour
A	Immersed in Isopropyl Alcohol one month
A	Immersed in Freon TF one hour
A	Immersed in Freon TF one month
A	Immersed in Freon TMC one hour
A	Immersed in Freon TMC one month
A	Immersed in 1, 1, 1 - Trichloroethane one hour
A	Immersed in 1, 1, 1 - Trichloroethane one month
A	Immersed in RMA Flux one hour
A	Immersed in RMA Flux one month

Property: Solvent Resistance

Dwell/Cure Time: 24 hr @ Room Temperature + 2 hr @ 160°F(71°C)

notes: Solvent resistance was determined using cured samples (1/2 in. x 4 in. x 1/8 in. thickness) immersed in the test solvent for 1 hour and 1 month. After the allotted period of time, the sample was removed and visually examined for surface attack as compared to the control. Key: A - Unaffected - no change to color or surface texture. B - Slight attack - noticeable swelling of surface. C - Moderate/severe attack - extreme swelling of surface.

3M™ EPX™ Pneumatic Applicator Delivery Rates

Pneumatic Applicator Delivery Rates	Test Condition
11.9 g/min	200 ml Applicator – Maximum Pressure 58 psi. 6mm Nozzle
46 g/min	200 ml Applicator – Maximum Pressure 58 psi. 10mm Nozzle
16.9 g/min	48.5/50 ml Applicator – Maximum Pressure 50 psi. 1/4 in. Nozzle

Property: Pneumatic Applicator Delivery Rates

notes: Tests were run at a temperature of 70°F ± 2°F (21°C ± 1°C) and at maximum applicator pressure.

3M™ Scotch-Weld™ Epoxy Adhesive DP190 Gray

Electrical and Thermal Properties

Glass Transition Temperature (Tg)		Test Condition
20 °C	68 °F	Mid-Point
7 °C	45 °F	Onset

Property: Glass Transition Temperature (Tg)

notes: Glass Transition Temperature (Tg) determined using DSC Analyzer with a heating rate of 68°F (20°C) per minute. Second heat values given.

Thermal Conductivity		
$90.9 \times 10^{-2} \text{ Cal/s/cm}^{\circ}\text{C}$	38.1 W/m/K	0.22 (btu-ft)/(h-ft ² -°F)

Property: Thermal Conductivity

Method: C177

Test Condition : 110°F on .25 inch samples

notes: Thermal conductivity determined using C-matic Instrument using 2 in. diameter samples.

Property	Values	Method	Test Condition	Notes
Dielectric Constant	6.5	ASTM D150	1 KHz, Room Temperature	
Dissipation Factor	0.09	ASTM D150	1 KHz, Room Temperature	
Volume Resistivity	$5.0 \times 10^{12} \Omega\text{-cm}$	ASTM D257	Room Temperature	
Coefficient of Thermal Expansion	62		Below Tg(41-68°F [5-20°C] range)	TCE determined using TMA Analyzer using a heating rate of 50°F (10°C) per minute. Second heat values given.
Coefficient of Thermal Expansion	177		Above Tg(167-284°F [75-140°C] range)	TCE determined using TMA Analyzer using a heating rate of 50°F (10°C) per minute. Second heat values given.

Handling/Application Information

Application Equipment

For smaller or intermittent applications, the 3M™ EPX™ Applicator is a convenient method of application.

For larger applications these products may be applied by use of flow equipment. Two part meter/mixing/proportioning/dispensing equipment is available for intermittent or production line use. These systems may be desirable because of their variable shot size and flow rate characteristics and are adaptable to many applications.

Handling/Application Information (continued)

Directions for Use

1. For high strength structural bonds, paints, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed. However, the amount of surface preparation necessary directly depends on the required bond strength and the environmental aging resistance desired by the user. For suggested surface preparations on common substrates, see the section on surface preparation.

2. Mixing

For Duo Pak Cartridges

3M™ Scotch-Weld™ Epoxy Adhesives DP190 Gray is supplied in a dual syringe plastic duo-pak cartridge as part of the 3M™ EPX™ Applicator system. To use, simply insert the duo-pak cartridge into the EPX applicator and start the plunger into the cylinders using light pressure on the trigger. Next, remove the duo-pak cartridge cap and expel a small amount of adhesive to be sure both sides of the duo-pak cartridge are flowing evenly and freely. If automatic mixing of Part A and Part B is desired, attach the EPX applicator mixing nozzle to the duo-pak cartridge and begin dispensing the adhesive. For hand mixing, expel the desired amount of adhesive and mix thoroughly. Mix approximately 15 seconds after uniform color is obtained.

For Bulk Containers

Mix thoroughly by weight or volume in the proportions specified in the typical uncured properties section. Mix approximately 15 seconds after uniform color is obtained.

3. For maximum bond strength, apply adhesive evenly to both surfaces to be joined.

4. Application to the substrates should be made within 75 minutes. Larger quantities and/or higher temperatures will reduce this working time.

5. Join the adhesive coated surfaces and allow to cure at 60°F (16°C) or above until completely firm. Heat up to 200°F (93°C) will speed curing. These products will cure in 7 to 14 days @ 75°F (24°C).

6. Keep parts from moving during cure. Contact pressure necessary. Maximum shear strength is obtained with a 3-5 mil bond line.

7. Excess uncured adhesive can be cleaned up with ketone type solvents.*

*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow manufacturer's precautions and directions for use.

Adhesive Coverage (typical): A 0.005 in. thick bondline will yield a coverage of 320 sqft/gallon.

3M™ Scotch-Weld™ Epoxy Adhesive DP190 Gray

Handling/Application Information (continued)

Surface Preparation

For high strength structural bonds, paint, oxide films, oils, dust, mold release agents and all other surface contaminants must be completely removed. However, the amount of surface preparation necessary directly depends on the required bond strength and the environmental aging resistance desired by the user.

The following cleaning methods are suggested for common surfaces:

Steel:

1. Wipe free of dust with oil-free solvent such as acetone, isopropyl or alcohol solvents.*
2. Sandblast or abrade using clean fine grit abrasives.
3. Wipe again with solvent to remove loose particles.
4. If a primer is used, it should be applied within 4 hours after surface preparation.

Aluminum:

1. Alkaline Degrease: Oakite 164 solution (9-11 oz./gallon water) at 190°F (87°C) ± 10°F for 10-20 minutes. Rinse immediately in large quantities of cold running water.*
2. Acid Etch: Place panels in the following solution for 10 minutes at 150°F (65°C) ± 5°F.*

Sodium Dichromate 4.1 - 4.9 oz./gallon

Sulfuric Acid, 66°Be 38.5 - 41.5 oz./gallon

2024-T3 aluminum (dissolved) 0.2 oz./gallon minimum

Tap water as needed to balance

3. Rinse: Rinse panels in clear running tap water.
4. Dry: Air dry 15 minutes; force dry 10 minutes at 150°F (65°C) ± 10°F.
5. If primer is to be used, it should be applied within 4 hours after surface preparation.

Plastics/Rubber:

1. Wipe with isopropyl alcohol.*
2. Abrade using fine grit abrasives.
3. Wipe with isopropyl alcohol.*

Glass:

1. Solvent wipe surface using acetone or MEK.*
2. Apply a thin coating (0.0001 in. or less) of 3M™ Scotch-Weld™ Metal Primer EC3901 or equivalent to the glass surfaces to be bonded and allow the primer to dry before bonding.

*Note: When using solvents, extinguish all ignition sources, including pilot lights, and follow manufacturer's precautions and directions for use.

Storage and Shelf Life

Store products at 60-80°F (15-27°C) for maximum shelf life.

These products have a shelf life of 24 months in their unopened original containers from date of manufacture.

Industry Specifications

UL 94 HB

Trademarks

3M, Scotch-Weld and EPX are trademarks of 3M Company.

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/company-us/all-3m-products/-/3M-Scotch-Weld-Epoxy-Adhesive-DP190-Gray?N=5002385+3293242432&rt=rud
Safety Data Sheet (SDS)	https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=DP190 Gray

3M™ Scotch-Weld™ Epoxy Adhesive DP190 Gray

Family Group

	DP190 Translucent	DP190 Gray
Time to Handling Strength (h) Substrate: Aluminum	6	8 to 12
Worklife (min) Test Condition: Room Temperature	80	90
Color Attribute Modifier: Cured	Translucent	Gray

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Precautionary Information

Refer to Product Label and Material Safety Data Sheet for health and safety information before using this product. For additional health and safety information, call 1-800-364-3577 or (651) 737-6501.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

