

Recomendación de transferencia y lavado

		STANDARD PRODUCTS																				PRINTABLES PRODUCTS																
		Standard	Nylon*	POLI-FLEX® PREMIUM	POLI-FLEX® BLOCKOUT	POLI-FLEX® NYLON	POLI-FLEX® STRETCH	POLI-FLEX® SPORT	TUBITHERM	TUBITHERM NEON COLOURS	POLI-FLEX® 5001 BLOCKOUT WHITE	POLI-FLEX® IMAGE REFLEX SILVER 4781 / REFLEX ECO 4782	POLI-FLEX® 4214 / 4215 DIMENSION	POLI-FLEX® IMAGE BRILLANT 4212 / 4213	POLI-FLEX® IMAGE LUMINOUS 421 / 431	POLI-FLEX® GLITTER	POLI-FLEX® PEARL GLITTER	POLI-FLEX® IMAGE PAINT / GLOSSY	POLI-FLEX® IMAGE / STARFLEX	TURBO PRINT 4036 MATT	ULTIMATE PRINT 4030 / 4032 MATT / 4031 GLOSS	ULTIMATE PRINT SOFT 4030 / 4034 MATT	ULTIMATE PRINT SUPERSOFT 4025	ULTIMATE PRINT TRANSPARENT SOFT 4035	POLI-FLEX® 4010 BLOCKOUT	POLI-FLEX® 4015 / 4016	POLI-FLEX® 4600 / 4605	POLI-FLEX® 4625 / 4626	POLI-FLEX® 4665 METALLIC	SUBLI-FLOCK 5901 / TUBITHERM PES	SOLVENT-FLOCK 5905							
CONDICIONES DE APLICACIÓN	Temperatura (°C)	160	160	150	160	130	Standard 160 150 130	Nylon* 150	160	160	160	150	160	160	160	160	160	160	160	160	160	160	160	160	160	160	160	160	160	160	160	160	160					
	Presión (bar)	2,5 – 3,0	2,5 – 3,0	2,0	2,5 – 3,0	2,5 – 3,0	2,5 – 3,0	2,0	2,0	2,0	2,5 – 3,0	2	3,0	2,5 – 3,0	2,5 – 3,0	2,5 – 3,0	2,5 – 3,0	2,5 – 3,0	2,5 – 3,0	2,5 – 3,0	2,5 – 3,0	2,5 – 3,0	2,5 – 3,0	2,5 – 3,0	2,5 – 3,0	2,5 – 3,0	2,5 – 3,0	2,5 – 3,0	2,5 – 3,0	2,5 – 3,0								
	Tiempo (seg.)	15	15	Prensar al textil 4 Prensar de nuevo 10	15	10	3 4 5	5 + 10*	15	15	15	15	25	15 Prensar de nuevo 3	15	15	15	15	15	15	15	15	15	15	15	15	15	15	15	15	15							
	Peel (Caliente = C / Frio = F)	C	C	C	C	C	C & F	C & F	C	F	C	C	F	F	F	C	C	C	C	C	C	C	C	C	F	C	F	C	C	C								
LAVADO	Resistencia al lavado (°C)	80	60	40	80	40	60	40	60	40	40	60	40	Lavado a mano	60	60	60	60	60	60	40	80	60	40	40	40	40	60	60	40	90	60	40					
	Adecuado para la secadora	●			●	●	●**		●	●	●	●		●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●						
	Limpieza química	●	●		●	●	●	●		●				●			●																					

*POLI-FLEX® TURBO & TURBO PRINT

- Prensar al textil para 5 seg.
- Prensar el material para 5 seg. y quitar el soporte
- Prensar para 10 seg. de nuevo

** POLI-FLEX® TURBO
TURBO PRINT
secador comercial hasta 100°C