

CLASSIFICATION OF REACTION TO FIRE PERFORMANCE IN ACCORDANCE WITH EN 13501-1:2018

Classification no.	2021-Efectis-R000777
Sponsor	Avery Dennison Materials Europe BV Willem Einthovenstraat 11 2342 BH OEGSTGEEST The Netherlands
Product name	Avery Dennison MPI 3026 Matt high opacity version (HOP)
Prepared by	Efectis Nederland BV
Notified body no.	1234
Author(s)	G. van der Lee M.Sc. B.R. Knottnerus B.Sc. A.H.L.M. Zwinkels B.Sc.
Project number	ENL-21-000331
Date of issue	August 2021
Number of pages	5

1. INTRODUCTION

This classification report defines the classification assigned to **Avery Dennison MPI 3026 Matt high opacity version (HOP)** in accordance with the procedures given in EN 13501-1:2018.

2. DETAILS OF CLASSIFIED PRODUCT

2.1 GENERAL

The product, **Avery Dennison MPI 3026 Matt high opacity version (HOP)**, will be used on various super wide format printers.

2.2 MANUFACTURER

Avery Dennison Materials Europe BV
Willem Einthovenstraat 11
2342 BH Oegstgeest
The Netherlands

2.3 PRODUCT DESCRIPTION

According to the sponsor the product is composed of:

- Face film: 95 μm , 125 g/m^2 ;
monomeric calendered vinyl;
Color: Opaque white matt film.
- Adhesive: 25 μm , 23 g/m^2 , permanent, clear, acrylic based;
- Backing paper: clay coated kraft paper, 125 g/m^2 .

The product has a total thickness of approx. 115 μm and a mass per unit area of approx. 148 g/m^2 .

More information on the product is available in the test report 2021-Efectis-R000775.

3. STANDARDS, REPORTS, RESULTS AND CRITERIA IN SUPPORT OF THIS CLASSIFICATION

3.1 APPLICABLE (PRODUCT) STANDARDS

EN ISO 11925-2:2020	Reaction to fire tests - Ignitability of products subjected to direct impingement of flame - Part 2: Single-flame source test
EN 13823:2020	Reaction to fire tests for building products - Building products, excluding floorings exposed to the thermal attack by a single burning item
EN 13238:2010	Reaction to fire tests for building products - Conditioning procedures and general rules for selection of substrates
EN 13501-1:2018	Fire classification of construction products and building elements Part 1: Classification using data from reaction to fire tests

3.2 REPORTS

Name of Laboratories	Name of sponsor	Report ref. no.	Test method
Efectis Nederland BV THE NETHERLANDS	Avery Dennison Materials Europe BV THE NETHERLANDS	2021-Efectis-R000775 2021-Efectis-R000774	EN ISO 11925-2:2020 EN 13823:2020

3.3 TEST RESULTS

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – maximum	Compliance with parameters
EN ISO 11925-2				
Surface flame impingement	Fs ≤150 mm	6	25	-
	Ignition of filter paper		-	Compliant
Edge flame Impingement	Fs ≤150 mm	6	25	-
	Ignition of filter paper		-	Compliant

Test method and test number	Parameter	No. tests	Results	
			Continuous parameter – mean (m)	Compliance with parameters
EN 13823				
	FIGRA _{0.2MJ} [W/s]	3	46	-
	FIGRA _{0.4MJ} [W/s]		9	-
	THR _{600s} [MJ]		0.9	-
	LFS < edge		-	Compliant
	SMOGRA [m ² /s ²]		11.4	-
	TSP _{600s} [m ²]		42	-
	Flaming debris - flaming ≤ 10 s - flaming > 10 s		- -	Compliant Compliant

3.4 CLASSIFICATION CRITERIA

Fire classification of construction products and building elements Excluding floorings and linear pipe thermal insulation products			
Classification criteria			
Class Test method(s)	B	C	D
EN ISO 11925-2 Exposure = 30 s	F _s ≤ 150 mm within 60 s Ignition of the paper in EN ISO 11925-2 results in a d2 classification.		
EN 13823	FIGRA _{0.2 MJ} ≤ 120 W/s LFS < edge of specimen THR _{600s} ≤ 7.5 MJ	FIGRA _{0.4 MJ} ≤ 250 W/s LFS < edge of specimen THR _{600s} ≤ 15 MJ	FIGRA _{0.4 MJ} ≤ 750 W/s
Additional classification			
Smoke production	s1 = SMOGRA ≤ 30 m ² /s ² and TSP _{600s} ≤ 50 m ² ; s2 = SMOGRA ≤ 180 m ² /s ² and TSP _{600s} ≤ 200 m ² ; s3 = not s1 or s2		
Flaming Droplets/particles	d0 = no flaming droplets/ particles in EN 13823 within 600 s; d1 = no flaming droplets/ particles persisting longer than 10 s in EN 13823 within 600 s; d2 = not d0 or d1.		

4. CLASSIFICATION AND FIELD OF APPLICATION

4.1 REFERENCE OF CLASSIFICATION

This classification has been carried out in accordance with clause 11 of EN 13501-1:2018.

4.2 CLASSIFICATION

The product, **Avery Dennison MPI 3026 Matt high opacity version (HOP)**, in relation to its reaction to fire behaviour is classified:

B

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming droplets / particles is:

d0

Reaction to fire classification: B – s1, d0

4.3 FIELD OF APPLICATION

This classification is valid for the following product parameters:

Thickness	115 μm
Surface density	148 g/m^2
Other properties	Product as described in §2.3

This classification is valid for the following end use applications:

Substrate	Steel sheet, thickness approx. 1.2 mm (class A1/A2 according to EN 13238:2010)
Air gap	Including 40 mm air gap
Methods and means of fixing	Glued using the products adhesive
Joints	Vertical only
Other aspects of end use conditions	Used on various super wide format printers

4.4 DURATION OF THE VALIDITY OF THIS CLASSIFICATION REPORT

Consult classification standard and national laws and regulations for limitations on the period of validity of the classification.

5. LIMITATIONS

This classification document does not represent type approval or certification of the product.



G. van der Lee M.Sc.
Junior project leader Reaction to Fire



A.H.L.M. Zwinkels B.Sc.
Project leader Reaction to Fire



B.R. Knottnerus B.Sc.
Project leader Reaction to Fire