

ESPUMA ACRILICA TIPO VHB TRANSPARENTE.

Liner de PE rojo translucido.

Grosor 0.5mm/1mm/1.5mm

DESCRIPTION	UNIT	VALUE	TEST METHOD
Adhesive		Acrylic	
Carrier		Acrylic Foam	
Color		Transparent	
Thickness	Mm	1,0 ± 0,05mm	
Release Liner		Red PE	
Standard Roll Width	Mm	800	
Standard Roll Length	M	33	

180° Peel Adhesion:

To Stainless Steel At Room Temperature	N/25mm	≥35	ASTM D-3330
--	--------	-----	-------------

Holding Power:

To Stainless Steel Temperature 80° C Static Load: 1000 g	Hour	>24	ASTM D-3654
--	------	-----	-------------

Dynamic Shear Strength:

To Stainless Steel At Roo, Temperature after 20 minutes	Kgf / cm2	≥3	ASTM D-1002
To Stainless Steel At Room after 24 hours	Kgf / cm2	≥ 4	ASTM D-1002

Temperature Tolerance:

Short Term 4 hours conditioning at indicated temperature with 100g sta tic load	° C	160	
Long Term Maximum Temperature where tape support 250g in static shear for 10.000 minutes	° C	100	