Shanghai Unisign Industrial Material Co., Ltd.
Taihong R&D Park, 59 Shennan Rd., Minhang, Shanghai, China
Tel: 0086-21-54179996, 0086-21-54178887 Fax: 0086-21-54176661
Email: sales@unisignflex.com Website: http://www.unisignflex.com/

Test Report

Opaque Self Adhesive Vinyl (SAV12OPTH/140GDP)

****

Test Items	***Result***
PVC Film	
Compositon:	White Calendered Monomeric PVC film, **Opaque**
Thickness(GB/T6672-2001):	100 um
Expected Outdoor Durability:	1 year
Adhesive	
Adhesive Type:	High Tack, Permanent Glue, Clear Glue
Glue weight (GB/T4669-1995):	29g
UV-resistance:	Good
Temperature Range (DIN53372):	－20℃～60℃
Final Tack (Test while adhering to stainless steel):	≥72 hours
180 degree peeling force(after 20 Minutes):	13 N/25mm
180 degree peeling force(after 24 hours):	15 N/25mm
Release Paper	
Type:	Double PE Coating
Color:	White
Liner weight (GB/T4669-1995):	140g
Shelf Life:	1 Year
Temperature resistance:	-20 to 60 degree

Storage temperature should not exceed 30 degree. And 24 degree is considered as ideal storage temperature.
50%--60% Relative Humidity is considered as ideal for storage
Away from direct Sunshine
Vertically hung is considered as ideal way for storage
5% technical tolerance is allowed

**********END**********

Declaration:

Please choose UNISIGN products suitably according to relative provisions or industrial standards. UNISIGN bears the responsibility for the specified technical and performance data on this page only. UNISIGN is not responsible for any other liability. (The technical data on this page is calculated on average, and ±5% tolerance is acceptable.)